

## **PRODUCT DATA SHEET**

## <u>Hi Temperature Disc Brake Wheel Bearing Grease, 14 Wt Oz</u> Part Number: SL3160

Product Description	A very stable resistant Aluminum Complex grease. Contains rust & oxidation inhibitors, anti-wear and extreme pressure additives & fortified with "moly" and graphite. For use in automotive disc/drum brakes, chassis and suspension systems
Applications	Automotive applications, ball joints, bearings, chassis points, construction ball & roller bearings, conveyor bearings, disc-brake systems, farm equipment, guides, mining applications, press rolls, roller bearings, slides, wheel bearings
Unit Package Description	14 Ounce Cartridge
Brand	Sta-Lube
Generic Description 1	Hi-Temp Disc Brake Wheel Grease
Net Fill	14 Wt Oz
UPC Code	072213316001
Unit Dimensions	9.31H x 2.13W x 2.13D in
Units Per Case	10
Case Dimensions	9.5H x 4.5W x 11.38D in
Cases Per Pallet	150
Case Weight	11 lbs
I 2 of 5 Code	30072213316002
Appearance	Dark Gray Semi-Solid to Solid Grease
Base Type	Aluminum Complex
Flash point (F)	>450°F
Flash point (C)	>232°C
Flammability Class - CPSC	None
Spec Gravity Concentrate	0.9 at 60°F
NLGI Grade	2
Timken OK Load [Lbs.]	60 Lbs
Plastic Safe	Not Determined



CRC Industries is a worldwide leader in the production of specialty chemicals for maintenance and repair professionals serving industrial, electrical, aviation, automotive and marine markets. CRC is ISO 9001:2008 certified and adheres to the strictest guidelines for quality in all facets of research, development and production.



CRC<sup>®</sup>, K&W<sup>®</sup>, Sta-Lube<sup>®</sup>, Marykate<sup>®</sup> and products denoted with <sup>®</sup> and <sup>™</sup> are trademarks of CRC Industries, Inc. Last revised: 5/4/2016 Page 1 of 2



HIGH TEMP SC BRAKE BEARING GREASE

> Part No. SL3160 14 OZ (397G)



## **PRODUCT DATA SHEET**

Even evention Dete	0.01 (Dutul Asstate 1)
Evaporation Rate	<0.01 (Butyl Acetate=1)
Working Temp (F)	0 to 325°F
Working Temp (C)	-18 to 162.5°C
4 Ball EP	315 Kg Weld,30 LWI
4 Ball Wear	0.75 mm
Drop Point	500°F
Elastomer Compatibility	0 to 30% vol; 0 to 15 hard
Leakage	10g Max
Oil Separation	<10%
Oxidation Stability	2 to 3
Pour Point (F)	0°F
Pour Point (C)	-17.78°C
ISO Viscosity Grade	205
Water Washout	<15%
Worked Penetration	265 to 295
Propellant	None
DOT Proper Shipping Name	Not Regulated
VOC % (Federal)	0.4
VOC g/L (Federal)	3.6
VOC Lbs./Gal. (Federal)	0.03
VOC Category	Not Regulated
Removal (How To)	Remove with a degreaser or brake cleaner product.



RING GREAS

Ξ



Last revised: 5/4/2016





 $CRC^{\circledast}, K\&W^{\circledast}, Sta-Lube^{\circledast}, Marykate^{\circledast} and products denoted with <math display="inline">^{\circledast}$  and  $^{m}$  are trademarks of CRC Industries, Inc.

Page 2 of 2